

General Purpose Silicone Rubber Sheetting

The general purpose range was specifically designed as a calandered grade for producing continuous solid sheetting. This is primarily used for belting and gaskets. The product has excellent resistance to ozone, oxidation, ultraviolet light, corona discharge, cosmetic radiation, radiation and weathering in general. Typical radiation resistance is greater than 105 grays.

Approvals

Please check individual datasheets - FDA Standard 21 CFR 177.2600, BFR XV, EU 1935/2004, WRAS, FAR 25/ JAR 25 /CS 25 Horizontal Flammability Tests and Automotive Standard Part 571MVSS302, REACH and RoHS.

Operating temperature range: -60°C to 230°C

Physical Property	Test Method	Units	Typical Values
Hardness	ASTM D412	ShA	60
Elongation at Break	ASTM D412	%	400
Tensile Strength	ASTM D412	MPa	10
Tear Resistance	ASTM D412	kN/m	22
Compression Set 24hrs @150		%	13
Brittle Point	ASTM D746	°C	-80
Thermal Conductivity	VDE 0304	W.m ⁻¹ .K. ¹	0.24
Limiting Oxygen Index	BS 2782 Part 1	%	24
Radiation Resistance		Grays	>105
Dielectric Strength	VDE 0303	kV.mm-1	23
Dielectric Constant	VDE 0303		2.9
Dissipation Factor	VDE 0303		3x10 ⁻⁴
Volume Resistivity	VDE 0303	ohms.cm	3x10 ¹⁵

Although the technical details and recommendations made correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use Polymax products must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product. All sales subject to our standard terms www.polymax.co.uk/sales-terms